

WLT- 001B Flexible Graphite Sheet with tanged 0.1mm SS304 inserted Graphite sheet + 0.10mm Tanged SS304 + Graphite sheet

Introduction

WLT- 001B Reinforced Graphite Composite Sheet is made from flexible graphite sheet reinforced with a single insertion of tanged 0.10 mm thick 304 stainless steel. No adhesive is required to bond the graphite layers as the graphite material is fixed to the insert by small, sharp teeth, resulting in a sturdy gasket material which is relatively easy to process and handle.

Applications

This product is used frequently in flange connections for piping and machinery. Its wide temperature range and excellent stress retention make it extremely suitable for use in steam systems, in the chemical and petrochemical industries, processing industry, etc. Reinforced Graphite Composite Sheet is mainly used for making cylinder gaskets of engines and punching into all kinds of sealing gaskets.

Technical data

Property		Standard	value
Thickness	mm		1.0 to 3.0
Density(graphite sheet)	g/cm ³		1.0
Temperature	°C	In oxidizing media	-200°C to +550°C
Max. pressure	bar		140
Sulphur content	ppm		<1500
Chloride content	ppm		<50
Compressibility	%	ASTM F36A-66	30-40
Recovery	%	ASTM F36A-66	≥15

Standard Size

Length: 1000mm, 1500mm Width: 1000mm, 1500mm Thickness: 1.0mm to 3.0mm